



SilGrip* PSA518

SilGrip* PSA518

Description

PSA518 silicone pressure sensitive adhesive is a xylene solution of phenyl based polysiloxane gum and resin. It is supplied at 56 percent silicone solids and may be further diluted with aromatic, aliphatic or chlorinated solvents. PSA518 may be blended with SR545 resin dispersion to obtain specific performance properties. PSA518 adhesive has been found useful in coating of film and fabric substrates for manufacturing industrial pressure sensitive tapes. May be an excellent choice for electrical insulation tapes and masking tapes used in electronic and plasma/flame spray applications due to its superior thermal stability.

Key Features and Benefits

- Wide temperature range performance, maintains good shear and tack properties at intermittent temperatures up to 550 ° F
- Adhesion to a wide variety of surfaces including low energy surfaces (silicones, fluoropolymers, polyolefines)
- Resistance to moisture, weathering (ozone, sunlight), chemical (acids, alkalis, oils, flux, reverse current stripping) and biological (fungus) attack
- Excellent balance of tack, peel adhesion, lap shear and creep resistance
- Excellent electrical properties

Typical Physical Properties

Property	Value
Silicone Solids, %	56
Specific Gravity, 25C	0.99
Viscosity @ 25° C (77° F), cps (Brookfield RVF, #6, Spindle @ 10 rpm)	65,000
Color	Light Straw
Flash Point (ASTM D93), °C (°F)	12 (54)
Solvent	Xylene

TYPICAL CURED ADHESIVE PROPERTIES

- Peel Adhesion⁽¹⁾, oz/inch | 37

■ Tack ⁽²⁾ , g/cm ²	910
---	-----

- (1) 1.5 mil dry adhesive thickness, 1mil polyester film, 1.5% benzoyl peroxide⁽³⁾, curing cycle: 10 min air dry, 90 sec at 177°C
- (2) Polyken Tack Tester, 100g weight, 0.5 sec dwell time, 0.5 cm/sec draw speed, 1.5 mil dry adhesive thickness, 1mil polyester film, 1.5% benzoyl peroxide⁽³⁾, curing cycle: 10 min air dry, 90 sec at 177°C
- (3) Luperox® A98 from Elf Atochem North America, Inc.

The properties of a cured silicone adhesive are affected by several factors such as type and amount of catalyst, cure cycle, adhesive thickness and backing type and thickness. Higher catalyst concentration will increase cohesive strength of the adhesive and improve shear strength, but it will reduce its adhesive strength resulting in lower tack and peel values. Typical peel adhesion values for various substrates, adhesive build and benzoyl peroxide concentrations are listed in Table 1.

TABLE 1

Typical peel adhesion values of PSA518 adhesive coated tapes per ASTM-D-1000:

Substrate	% BPO on Solids	Adhesive Build In mils	180° Peel oz/inch
2 mil Mylar*	0	1.5	65 to 70
2 mil Mylar	0	2.0	67 to 72
2 mil Mylar	1.0	1.5	52 to 57
2 mil Mylar	1.0	2.0	55 to 59
2 mil Mylar	2.0	1.5	50 to 53
2 mil Mylar	2.0	2.0	52 to 54
2 mil Teflon**	0	1.5	45 to 47
2 mil Teflon	0	2.0	50 to 55
2 mil Teflon	1.0	1.5	40 to 52
2 mil Teflon	1.0	2.0	42 to 45
2 mil Teflon	2.0	1.5	33 to 36
2 mil Teflon	2.0	2.0	36 to 38
3 mil Glass	0	2.3	38
3 mil Glass	2.0	2.0	27

* MYLAR is a Registered Trademark of DuPont

** TEFLON is a Registered Trademark of DuPont

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

The warranty period is 6 months from date of shipment from Momentive Performance Materials if stored in the original unopened container at 25°C (77°F).

Customers should review the latest Material Safety Data Sheet (MSDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, and any special storage conditions required for safety. MSDS are available at www.momentive.com or, upon request, from any Momentive Performance Materials (MPM) representative. **For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center.** Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Processing Recommendations

Application

PSA518 silicone adhesive is supplied at a viscosity suitable for conventional tape coating equipment. If necessary, it may be thinned with toluene, xylene or other compatible solvents. After the adhesive is applied to the backing, it is exposed to a two step process: solvent removal and curing.

Solvent Removal

To achieve optimum adhesive properties, it is essential to optimize the drying step of the process in order to assure that the solvent is removed from the adhesive film before the curing step of the process starts. Improper drying will result in residual solvent entrapment within the adhesive. If the adhesive is then exposed to temperatures higher than 93.5° C (200°F), decomposing peroxide catalyst can cause crosslinking reaction between solvent and adhesive through methyl groups on siloxane chains and on solvent molecules and adversely affect the properties of the adhesive. Typical temperature range for the drying step of the process is 83 °C (180 °F) to 90 °C (194 °F). A typical drying cycle is 2 minutes at 90 °C (194 °F).

Curing Process

Once the solvent is removed from the adhesive film, the peroxide cure should be initiated by exposure to heat. A typical curing cycle is 2 minutes at 165 °C (329 °F). Longer exposure time and higher temperature, up to 204 °C (400 °F), can be used without adverse effects. The exact conditions required to achieve a complete cure will depend on oven length and efficiency, peroxide type and type of substrate used, and should be established during experimental trials on the machine.

Catalysts

High purity, 98% benzoyl peroxide ⁽³⁾ in the quantity of 1 to 3% based on silicone solids, has been found to give the most consistent results in curing of silicone pressure sensitive adhesives. In applications requiring low temperature cure, 2,4 -dichlorobenzoyl peroxide, which is activated at 132 °C (270 °F), can be used. It should be noted that 2,4-dichlorobenzoyl peroxide may generate polychlorinated biphenyls during the curing process. Please refer to Code of Federal Regulations, title 40, part 761 regarding incidental PCB byproducts if 2,4- dichlorobenzoyl peroxide is utilized.

The peroxide should be dispersed in solvent before it is mixed with the adhesive. Thorough mixing of the peroxide and adhesive to achieve homogeneous dispersion is essential for consistency of finished product.

(3) Available from: Elf Atochem North America, Inc.,

Priming

In certain applications, the anchorage of the adhesive to the backing may be insufficient and the coating of a primer prior to the adhesive coating may be required.

A typical formulation for a primer may be found in Table 2 below. The formulation may need to be adjusted depending on required bath life, coating equipment and backing material. The primer may be coated by direct gravure, wire wound rod or other coating technique suitable for solvent based coatings, and must be cured prior to adhesive application. The curing conditions will depend on equipment capabilities, substrate type and formulation used and should be established during experimental trials on the machine.

Table 2. Typical Primer ⁽⁴⁾ Formulation

Component	Parts by Weight
SS4195A-D1	13.30
SS4191B	0.16
SS4192c	0.50
SS4259c	0.30
Solvent ⁽⁵⁾	85.74

(4) Refer to document #CDS5511, SS4195-D1 Primer for Phenyl Based Silicone Pressure Sensitive Adhesives, for more information

(5) Typical solvents: toluene, heptane, toluene/heptane mixtures

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

From automotive to healthcare, from electronics to construction, products from Momentive Performance Materials Inc. are practically everywhere you look. We are a global leader in silicones and advanced materials with a 70+ year heritage of innovation and being first to market – with performance applications that improve everyday life. By knowing our customers’ needs and creating custom technology platforms for them, we provide science based solutions to help customers increase performance, solve product development issues and engineer better manufacturing processes.

Contact Information

For product prices, availability, or order placement, contact our customer service by visiting www.momentive.com/Contacts

For literature and technical assistance, visit our website at: www.momentive.com

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.

DISCLAIMER

The information provided herein was believed by Momentive Performance Materials Inc. (collectively with its subsidiaries, “Momentive”) to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for user’s intended application or use. All products supplied by Momentive are subject to Momentive’s standard terms and conditions of sale. **MOMENTIVE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY MOMENTIVE**, except that the product shall conform to Momentive’s specifications. Nothing contained herein constitutes an offer for the sale of any products.