

# **Product Data**

## **Octamethylcyclotetrasiloxane XF3803**

XF3803 is octamethylcyclotetrasiloxane for industrial use.

### **TYPICAL PROPERTY DATA**

<b>PROPERTIES</b>		
Appearance		Colorless, transparent liquid
Viscosity (25°C)	mm <sup>2</sup> /s	2.4
Boiling point	°C	175
Freezing point	°C	17
Flash point	°C	52
Refractive index (n <sub>D</sub> <sup>25</sup> )		1.394
Surface tension	mN/m	19.0
Specific gravity (25°C)		0.95
Vapor pressure (20°C)	Pa	100
CAS Number		556-67-2

*Typical property data values should not be used as specifications.*

### **HANDLING AND SAFETY**

- ◆ Use the product in a well ventilated area.
- ◆ Wear eye, hand and respiratory protection when in handling.
- ◆ Maintain adequate ventilation in the work place at all times.
- ◆ For electrostatic prevention, have equipment and devices grounded.

### **STORAGE**

- ◆ Store in a dry and cool place out of direct sunlight.
- ◆ Keep out of the reach of children.

### **PACKAGING**

- ◆ 190kg drum available

---

**FOR INDUSTRIAL USE ONLY**

*It is the responsibility of the user to determine the suitability of any Momentive Performance Materials Japan product for any intended application. NEVER USE ANY MOMENTIVE PERFORMANCE MATERIALS JAPAN PRODUCT FOR IMPLANTATION OR INJECTION INTO THE HUMAN BODY. Specifications are available by contacting Momentive Performance Materials Japan. Typical property data values should not be used as specifications. Inasmuch as Momentive Performance Materials Japan LLC has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own tests to determine the suitability of the material for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any Momentive Performance Materials Japan patent covering use or as recommendations for use of such materials in the infringement of any patent. Material Safety Data Sheets are available upon request from Momentive Performance Materials Japan. The contents of this catalog are subject to change without notice. No part of this data may be reproduced without the prior approval of Momentive Performance Materials Japan.*

---



**Momentive Performance Materials Japan LLC**

<http://www.momentive.com>

Technical Answer Center (Japan): Phone: +81-276-20-6182 FAX: +81-276-31-6259  
Tokyo Head Office: Phone: +81-3-5544-3111 FAX: +81-3-5544-3122